

SiSiB[®] PC1251 SILANE

- 1 -

CHEMICAL NAME

Aminoethylaminomethyltriethoxysilane

Synonym: N-(2-aminoethyl)-aminomethyltriethoxysilane

N-(triethoxysilylmethyl)ethylenediamine

CHEMICAL STRUCTURE

INTRODUCTION

SiSiB® PC1251 is is a bifunctional organosilane possessing two reactive amino groups and hydrolyzable inorganic ethoxysilyl groups. Due to the nature of its amino group, this substance reacts as a strong base. The silane hydrolyzes autocatalytically in the presence of moisture (ethanol is released) to form silanols, which can then react with themselves to produce siloxanes or can bind to inorganic substrates. As a bifunctional organosilane, it can bind to both inorganic materials and organic polymers to function as a molecular bridge between organic and inorganic substrates.

The close proximity of the nitrogen atom to the silicon atom can accelerate hydrolysis reaction compared to (amino-propyl)silanes.

APPLICATIONS

SiSiB® PC1251 can be used as an adhesion promoter in sealants, adhesives and coatings.

SiSiB® PC1251 can be used as a surface modifier for fillers.

SiSiB® PC1251 can be used in the production of silyl-modified polymers which serve as binders in adhesives and sealants.



Copyright© 2009 Power Chemical Corporation Ltd. SiSiB® is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia



SiSiB[®] PC1251 SILANE

- 2 -

TYPICAL PHYSICAL PROPERTIES

CAS No.	N/A
EINECS No.	N/A
Formula	$C_9H_{24}N_2O_3Si$
Molecular Weight	236.38
Boiling Point	256°C [760mmHg]
Flash Point	109°C
Color and Appearance	Clear to straw liquid
Density _{25/25°C}	0.967
Refractive Index	1.443 [25°C]
Purity:	Min.97.0%

PACKING AND STORAGE

SiSiB® PC1251 is supplied in 200Kg steel drum or 1000Kg IBC container.

In the unopened original container SiSiB® PC1251 has a shelf life of one year in a dry and cool place.

Notes

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: silanes@SiSiB.com.



Copyright© 2009 Power Chemical Corporation Ltd. SiSiB® is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia